

3M™ Scotchcast™ Electrical Resin 5230N

One Part, Epoxy Powder Resin

- Specially formulated for use in electrostatic fluid bed process
- Excellent electrical properties
- Excellent heat, chemical and moisture resistance
- Superior cut-through resistance
- UL 1446 electrical insulation systems approval at Class-155(F)

3M™ Scotchcast™ Electrical Resin 5230N is a widely used, general purpose epoxy powder resin. A one-part, blue pigmented, rapid heat-curing product, it is designed to provide a continuous, tough moisture and chemical resistant dielectric coating to a variety of substrates.

Scotchcast™ 5230N is manufactured by a fusion blend process, insuring that each individual particle of powder contains all the components necessary to effect a complete cure and attain stated performance properties.

Scotchcast™ 5230N is applied to a cold object via the electrostatic fluid bed process. The negatively charged resin particles are attracted to the grounded object to be coated. Coating thicknesses up to 25 mils may be obtained. Because of its superior charging capabilities Scotchcast™ 5230N exhibits excellent slot penetration on motor stators and armatures. Uses for Scotchcast™ 5230N include moisture-proofing and insulating armatures, stators, buss bars and toroid cores.

Scotchcast™ Electrical Resin 5230N-Typical Properties

Property	Value
Color	Blue
Specific Gravity ¹ (cured)	1.60
Dielectrical Strength ³ 12 - 15 mil /30 µm to 375 µm coating	1000 v/mil (39 v/micron)
Thermal Shock ² 10 cycles - 75°C to 155°C 12 - 15 mil /30 µm to 375 µm coating 1/8" sandblasted steel	Passes
Impact Resistance ² 12 - 15 mil (305-375 µm) coating 1/8" blasted steel panel Gardner 5/8" Radius Impact Tester	160 inch-lbs /18.2J
Cut-through Resistance ² - 1 lb wt: 1/8 AWG wire	320°C (608°F)
Abrasion Resistance ⁵	.11 grams
Edge Coverage ² 12 - 15 mil /305 µm to 375 µm coating on flat	>35%
Gel Time ² @ 193°C hot plate	9-16 seconds
Thermal Conductivity ⁴	0.30 w/mk

*Not recommended for specification purposes. Product specifications will be provided upon request.

Test Methods

¹ ASTM D-792

² 3M Test Method

³ ASTM D-149

⁴ ASTM E-1530

⁵ ASTM D-4060



Usage Information

Method of Application

Before resin is applied, the object to be coated should be clean, dry and free of oils. Scotchcast™ Electrical Resin 5230N is first placed in an electrostatic fluid bed and charged (40 to 90KV), causing the epoxy resin particles to repel each other and move upward. This results in a cloud of charged particles above the surface of the bed. A grounded object is coated when passed through or placed in this cloud. Scotchcast™ 5230N can be deposited in film thicknesses up to 25 mils (635 microns) on objects at room temperature. Because it is applied to a room temperature substrate, the powder can be selectively removed. Air used for fluidizing should be dried to -20°F (-29°C) dew point.

Curing

The cure of Scotchcast™ 5230N is accomplished by heating the coated part to a temperature above the melting point of the resin. The resin then melts, flows to a controlled extent, and coalesces into a smooth, continuous, thin, essentially uniform coating, which cures and bonds to the substrate. The coating maintains its uniformity on flat surfaces as well as in corners and on high points of the part. Either convection oven or induction heating may be used as a heat source for curing the resin.

The figures below represent nominal guidelines for obtaining the resin's adhesion, impact and chemical resistance characteristics.

Cure Temperature	Time
177°C (350°F)	15 minutes
204°C (400°F)	6 minutes
232°C (450°F)	3 minutes

3M and Scotchkote are products of 3M Company.

Important Notice

All statements, technical information and recommendations related to 3M Products are based on information believed to be reliable, but the accuracy or completeness is not guaranteed. Before using the 3M Product, you must evaluate it and determine if it is suitable for your intended application. Because conditions of Product use are outside of our control and vary widely you assume all risks and liability associated with such use. Any Product-related statements not contained in current 3M publications, or any contrary statements contained in your purchase order, shall have no force or effect unless expressly agreed to in writing by an authorized officer of 3M.

Warranty; Limited Remedy; Limited Liability.

3M warrants that Product will conform to 3M published specifications upon shipment. If Product is proven not to have met the specifications your exclusive remedy and 3M's sole obligation will be, at 3M's option, to replace the Product or to refund the purchase price of the Product. **EXCEPT WHERE PROHIBITED BY LAW, THIS WARRANTY IS MADE IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR THOSE ARISING FROM A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE.** Buyer is an expert in its field and is responsible for determining if Products are suitable for a particular purpose or application. 3M has no obligation under this warranty with respect to any Product that has failed due to inadequate or improper storage, handling, surface preparation, application, or maintenance; failure to follow Product instructions; or alteration or damage to the Product caused by accident, neglect, or misuse. **EXCEPT WHERE PROHIBITED BY LAW, IN NO EVENT SHALL 3M BE LIABLE FOR ANY DIRECT, INDIRECT, SPECIAL, INCIDENTAL OR CONSEQUENTIAL LOSS OR DAMAGES (INCLUDING LOST PROFITS) ARISING FROM THIS PRODUCT, REGARDLESS OF THE LEGAL THEORY ASSERTED.**

Time does not include that required to reach the cure temperature. The user must determine the time required for the coated substrate to reach listed temperatures.

Handling and Safety Precautions

Read all Health Hazard, Precautionary, and First Aid statements found in the Material Safety Data Sheet and/or product label prior to handling or use.

Storage

Laboratory evaluation indicates that the usable shelf life of this product is twenty four (24) months from the date of manufacture when stored at temperatures not exceeding 16°C (60°F) providing the material is stored in its original container. Care should be taken when removing resin from the original shipping container to prevent inclusion of foreign material. After resin removal, the bag should be retied immediately. This will help to avoid agglomeration caused by excess moisture. For best results, store in a cool, dry place.

UL Recognition

Scotchcast™ 5230N has been evaluated by UL and is included in UL file #35075. It is recognized as class B component insulation. 5230N is also listed as integral ground insulation in a new 3M class F insulation system designated 3M155-2 under UL file #163090.

Ordering Information/Customer Service

For ordering technical or product information, or a copy of the Material Safety Data Sheet, call:
Phone: 800/722-6721
Fax: 877/601-1305



Infrastructure Protection Division

6801 River Place Blvd.
Austin, TX 78726-9000
www.3M.com/corrosion

Please recycle. Printed in US.
© 3M 2013. All rights reserved.
80-6111-8324-7-C