

RTV Silicones



ALL MG PRODUCTS ▾

Jump to Product Number

[Accessories](#)[Adhesives](#)[Brushes](#)[Cleaners / Degreasers](#)[Contact Cleaners](#)[Desoldering Braid](#)[Dusters & Circuit Coolers](#)[EMI / RFI Shielding](#)[Epoxies](#)[Flux and Flux Remover](#)[Glass & Screen Cleaners](#)[Isopropyl Alcohol](#)[Lead Free Solder](#)[Lubricants](#)[Potting & Encapsulating](#)[Protective Coatings](#)[Pens](#)[Prototyping Materials](#)[RTV Silicones](#)[Soldering/desoldering](#)[Specialized Cleaners](#)[Swabs](#)[Thermal Management](#)[Thermally Conductive](#)[Adhesives](#)[Wipes](#)RTV Silicones by MOMENTIVE
performance materials

1-Part Adhesive Sealant RTV118

▶ STOCKED ITEM

▶ BUY NOW

Primary Characteristics

- ▶ Clear Flowable
- ▶ Acetoxy cure
- ▶ Food Applications
- ▶ FDA 21 CFR 177.2600

Excellent for thin section potting, filling small surface voids, self leveling protective coatings. Will flow into small crevices and hard to reach places. Not for use in delicate electrical and electronic applications in which corrosion of copper, brass, or other sensitive metals is undesirable. Can be used in food contact applications where FDA 21 CFR 177.2600 regulations apply. Reference CDS4319 "Food Contact Applications", "Silicone Rubber Compounds."

Available Sizes

Catalog Number	Sizes Available	Description
RTV118-85ML	85 mL	Tube
RTV118-300ML	▶ SPECIAL ORDER 300 mL	Cartridge

Specifications

Use	Adhesive Sealant
Special Feature	High Performance
Standards	FDA 21CFR 177.2600
	MIL-A-46106, group 1, type 2
	UL File No. E-36952
Cross Reference	RTV112
Uncured Properties	
Consistency	Flowable
Color	Clear
Specific Gravity	1.05
Tack Free Time	20 min
Cure Time (77°F /50% relative humidity)	7 days
Useful Temp. Range	-60°C to 205°C (-75°F to 400°F)
Cured Properties - MECHANICAL	
Hardness	25 (Shore A)
Tensile Strength	2.20 MPa (325 psi)
Elongation	325%
Peel Strength	3 kg/cm (15 lb/in)
Cured Properties - ELECTRICAL	
Volume Resistivity	6 x 10 ¹⁴ ohm · cm
Dielectric Strength	16 kV/mm (400 V/mil)

Technical Support
for RTV Silicones

1-800-255-8886

M.G. Chemicals Disclaimer
for RTV Silicones >[Locate Distributor >](#)

Quick Links

- ▶ [MSDS](#)
- ▶ [Specifications](#)
- ▶ [Available Sizes](#)

Related products:

 [RTV112 White](#)

Resources

- ▶ [Selection Guide >](#)
- ▶ [One Part Chart](#)
- ▶ [Two Part Chart](#)

Find by Application

- [General Purpose >](#)
- [Aerospace >](#)
- [Marine >](#)
- [High Performance Assembly >](#)
- [Electronics >](#)
- [Thermal Conductivity >](#)
- [High Temperature >](#)
- [Low Temperature >](#)



Dielectric Constant	2.8 @ 60 Hz
Cured Properties - THERMAL	
Thermal Conductivity	0.21 W/m · °K
Brittle Point	-60°C (-75°F)
Thermal Expansion	27 x 10 ⁻⁵ (°C) ⁻¹
Other	
Viscosity (@ 25°C)	20,000 cps

[Return to top](#) ^

© 2000 - 2007 MG Chemicals. All rights reserved. [Site Map](#) [Terms & Conditions](#) [Contact Us](#)

web site design by offbeat studio