

## Heat Sink Compound – Grey Ultra Conductive 50g Jar

### Product Highlights

- **Lead-Free / RoHS 3 Compliant / REACH Compliant**
- Ultra High Density Thermal Paste. Grey, non-curing, flowable, thermally conductive heat sink compound. Heavily filled with heat-conductive metal oxide. Provides extremely high thermal conductivity, low bleed and high temperature stability.
- Electrically insulating ( $7 \times 10^{12}$  ohm-cm)

### Specifications

Viscosity:	95,000 cP (95,000 mPa·s)
Density:	2.5g/cc
Thermal Conductivity:	4.3 W/m·K
Thermal Resistance:	0.06 °C·cm <sup>2</sup> /W
Electrical Volume Resistivity:	$7 \times 10^{12}$ ohm-cm
Dielectric Strength:	0.67 MV/m (17V/mil)
Operating Temperature (Continuous):	-40 to 150°C (-40 to 302°F)
Operating Temperature (Peak):	200°C (392°F)
Operating Life:	>8 years *dependent on several factors, test in application to ensure suitability
Size:	50g Jar



### Storage and Handling

Store refrigerated or at room temperature 3-25°C (37-77°F). Allow 4 hours for thermal paste to reach an application temperature of 20-25°C (68-77°F) before use.

### Shelf Life

>24 months

### Stencil Life

>7 days @ 20-70% RH 22-28°C (72-82°F)

### Transportation

This product has no shipping restrictions. Shipping below 0°C (32°F) or above 25°C (77°F) for normal transit times by ground or air will not impact this product's stated shelf life.

**Chip Quik® Thermal Paste Orderable Part Numbers**

<b>Thermal Conductivity (W/m·K)</b>	<b>Thermal Resistance (°C·cm<sup>2</sup>/W)</b>	<b>Density (g/cc)</b>	<b>Color</b>	<b>Package</b>	<b>Size (g)</b>	<b>Orderable Part Number</b>
0.67	0.16	2.1	White	Syringe	10	TC1-10G
0.67	0.16	2.1	White	Syringe	20	TC1-20G
0.67	0.16	2.1	White	Jar	200	TC1-200G
4.3	0.06	2.5	Grey	Syringe	10	TC2-10G
4.3	0.06	2.5	Grey	Syringe	20	TC2-20G
4.3	0.06	2.5	Grey	Jar	50	TC2-50G
8.5	0.03	2.5	Grey	Syringe	1	TC3-1G
8.5	0.03	2.5	Grey	Syringe	3.5	TC3-3.5G
8.5	0.03	2.5	Grey	Syringe	10	TC3-10G