

Description

The *500 Series Copper Clad Boards* are made of a laminate consisting of continuous woven glass cloth impregnated with epoxy resin. The boards are made of FR4 which is a flame retardant version of G-10 material.

The boards are ideal for prototyping and small production runs. It is used by PCB manufacturers, design engineers, hobbyists, and students.

Benefits and Features

- **Complies with UL** (file number E214381) **and IPC-4101C/21**
- **DICY (dicyandiamide) Cured System**
- **Easy to cut with no specialized equipment required**
- **UV blocking**
- **Available in 1 oz (1.37 mil, 35 µm) and ½ oz (0.67 mil, 17 µm) copper cladding**
- **Comes in 1/16" (1.60 mm) and 1/32" (0.80 mm) laminate thicknesses**

Properties

<i>Physical Properties</i>	<i>Method</i>	<i>Specification</i>	<i>Value</i>
Moisture Absorption	IPC-TM-650 2.6.2.1	<0.80%	0.25%
Flammability	UL-94	94V-0	V0
<i>Thermal Properties</i>	<i>Method</i>	<i>Specification</i>	<i>Value</i>
Glass Transition Temperature (T _g)	IPC-TM-650 2.4.25	>110	140 °C
CTE prior T _g , z-axis	IPC-TM-650 2.4.24	—	50 ppm/°C
CTE after T _g , z-axis	"	—	250 ppm/°C
Total Expansion (50-260 °C), z-axis	"	—	3.75%
Time to Delamination T260	IPC-TM-650 2.4.24.1	—	20 min
Time to Delamination T288	"	—	2 min
Thermal Degradation via TGA	ASTM D 3850	—	310 °C
Thermal Stress @288 °C	IPC-TM-650 2.4.13.1	>10 s	300 s
Maximum Operating Temp. (MOT)	UL 94	—	130 °C

<i>Electrical Properties</i>	<i>Method</i>	<i>Specification</i>	<i>Value</i>
Volume Resistivity	IPC-TM-650 2.5.17.1	$>1 \times 10^6 \text{ m}\Omega\cdot\text{cm}$	$5 \times 10^8 \text{ m}\Omega\cdot\text{cm}$
After Moisture Resistance	"		
Surface Resistivity	"	$>1 \times 10^4 \text{ m}\Omega\cdot\text{cm}$	$5 \times 10^7 \text{ m}\Omega$
After Moisture Resistance	"		
Dielectric Constant @1 GHz	IPC-TM-650 2.5.5.9	<5.4	4.2
Dissipation Factor @1 GHz	"	>0.035	0.015
Dielectric Strength	IPC-TM-650 2.5.6.2	$>762 \text{ V/mil}$	1 200–1 400 V/mil
Dielectric Breakdown	IPC-TM-650 2.5.6	$>40 \text{ kV}$	60 kV
Comparative Tracking Index (CTI)	ASTM D 3638	—	Grade 3, 175–250 V
Arc Resistance	IPC-TM-650 2.5.1	$>60 \text{ s}$	240 s
<i>Mechanical Properties</i>	<i>Method</i>	<i>Specification</i>	<i>Value</i>
Peel Strength (1 oz)	IPC-TM-650 2.4.8	—	10-12 lb/in
As received	"		
After thermal stress	"	$>6 \text{ lb/in}$	9-12 lb/in
Flexural Strength	IPC-TM-650 2.4.4	$>415 \text{ MPa}$	600 MPa
Warp	"	$>345 \text{ MPa}$	500 MPa
Fill	"		

Note: Data shown are typical values for reference only.

Storage

Store at around room temperature 18 to 27 °C [65 to 80 °F] and protect from direct heat or sunlight. Keep sealed in an air tight container, away from humidity.

Health and Safety

Please see the **Safety Data Sheet** (SDS) for more details on transportation, storage, handling and other security guidelines.

Packaging and Supporting Products

1 oz Copper Claddings

FR4 1/16" (1.60 mm), single sided

<i>Cat. No.</i>	<i>Metric</i>	<i>Imperial</i> ^{a)}
503	76 x 127 mm	3" x 5"
506	101 x 152 mm	4" x 6"
509	152 x 152 mm	6" x 6"
515	203 x 254 mm	8" x 10"
521	304 x 304 mm	12" x 12"
580	914 x 1219 mm	36" x 48"

FR4 1/16" (1.60 mm), double sided

<i>Cat. No.</i>	<i>Metric</i>	<i>Imperial</i> ^{a)}
540	76 x 127 mm	3" x 5"
550	152 x 152 mm	6" x 6"
555	304 x 304 mm	12" x 12"



ISO 9001 Registered Quality System.
Burlington, Ontario, Canada QMI File # 004008

Copper Clad Boards 500 Series Technical Data Sheet

500 Series

FR4 1/32" (0.80 mm), single sided

<i>Cat. No.</i>	<i>Metric</i>	<i>Imperial</i> ^{a)}
588	152 x 228 mm	6" x 9"

a) Sizes are approximate

½ oz Copper Claddings

FR4 1/16" (1.60 mm), single sided

<i>Cat. No.</i>	<i>Metric</i>	<i>Imperial</i> ^{a)}
510	152 x 152 mm	6" x 6"
516	203 x 254 mm	8" x 10"

b) Sizes are approximate

FR4 1/32" (0.80 mm), double sided

<i>Cat. No.</i>	<i>Metric</i>	<i>Imperial</i> ^{a)}
587	101 x 152 mm	3" x 5"
589	152 x mm	4" x 6"

FR4 1/16" (1.60 mm), double sided

<i>Cat. No.</i>	<i>Metric</i>	<i>Imperial</i> ^{a)}
551	152 x 152 mm	6" x 6"

Technical Support

Contact us regarding any questions, improvement suggestions, or problems with this product. Application notes, instructions, and FAQs are located at www.mgchemicals.com.

Email: support@mgchemicals.com

Phone: +(1) 800-340-0772 (Canada, Mexico & USA)
+(1) 905-331-1396 (International)

Fax: +(1) 905-331-2862 or +(1) 800-340-0773

Mailing address: **Manufacturing & Support**
1210 Corporate Drive
Burlington, Ontario, Canada
L7L 5R6

Head Office
9347-193rd Street
Surrey, British Columbia, Canada
V4N 4E7

Disclaimer

This information is believed to be accurate. It is intended for professional end users having the skills to evaluate and use the data properly. *M.G. Chemicals Ltd.* does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.